


POLYURETHANE ROUND BELTS

TECHNICAL DATA SHEET

RU-4

COMPOSITION	
Material	Thermoplastic polyurethane (TPU)
Hardness	92 ±5 Sh.A
Colour	Green
Surface	Rough
Coefficient of friction on steel	0.4



Diameter		4.0	mm	0.16	in.
Weight		14.0	gr/m	0.01	lbs./ft.
Minimum pulley diameter		35.0	mm	1.38	in.
Pull for 8% elongation		30.0	N	6.7	lbf.
Temperature resistance (1) (1) Use of the belt with limit v	min. max values r	-20 60 may redu	°C	-4 140	°F °F
Humidity influence				no	
Permanent antistatic dynamically UNI EN ISO 21179				no	

FEATURES

- Extremely good tensile strengths
- Elasticity
- Flexibility values

COMPLIANCES

REACH EC 1907/2006 Regulation and Amendments

JOINTING SYSTEM

Being thermoweldable polyurethane it enables quick endless jointing of belts. For high precision joints of round belts of any size CHIORINO supply the **FAST JOINT welder "S15".**

SUITABLE FOR

Packaging

Printing and graphic

NOTES

Belts which are used in various markets for transmission of light duty drives, at medium low speeds and conveying light loads.

Last Update: 28-10-2013

PRODUCT CODE ES228

DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.