

11\_625

# SHEETING FOR VENEERING PRESSES

## **TECHNICAL DATA SHEET**

	LI-G25
TECHNICAL SPE	ECIFICATIONS
Material	Natural elastomer
Total thickness	$2.5 \pm 0.15 \text{ mm}$ 0.10 $\pm 0.006 \text{ in.}$
Weight	2.7 ± 0,15 kg/m <sup>2</sup> 0.55 ± 0.006 lbs./sq.ft
Outer surface pattern	Smooth
Inner surface pattern	FL
Colour	Brown
Hardness	45 ±5 Sh.A
Production width	2000 mm 79 in.
Temperature resistance (1) (1) use of the sheeting wit	min20°C -4 °F max. +120°C 248 °F th limit values may reduce its life
	PECIFICATIONS
Load at break	22 N/mm <sup>2</sup> 3191 lbs./sq.in - Hi
Elongation at break	- Cr - Te
Modulus at 50% str	
Tear strength	100 <sub>N</sub> 22 Ibs.
CHEMICAL RES	ISTANCES
- Good resistance to	o alcohols and glycols type Politherm 55 REA
- Fair resistance to	aqueous solutions of acids and alkalis

- Fair resistance to solvents, hydrocarbons, acids and concentrated alkalis, natural and synthetic oils, ozone

# 5 ity /ery nce

## NCES

NOTES

ation EC 1907/2006 and amendments

SUITABLE FOR

Wood: veneering panels

PRODUCT CODE LA9

Last Update: 28-10-2013

### DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.