

CONVEYOR AND PROCESS BELTS
TECHNICAL DATA SHEET
CODE NA1255
TYPE
2M10 U0-U2 N HC SP
COMPOSITION

Conveying surface	Material	Polyurethane (TPU)		
	Thickness	0.20 mm	0.008 in.	
	Surface pattern	Matt		
	Colour	Black		
	Coefficient of friction	LF		
Textile carcass	Material	Polyester (PET)		
	Plies no.	2		
	Weft type	Rigid		
Driving surface	Material	Fabric with polyurethane (TPU) impregnation		
	Thickness	---	mm	---
	Surface pattern	Fabric		
	Colour	Grey		

TECHNICAL SPECIFICATIONS

Total thickness	1.20 mm	0.05 in.
Weight	1.40 kg/m ²	0.29 lbs./sq.ft
Elongation at 1%	10 N/mm	57.0 lbs./in.
Max. admissible pull	10 N/mm	57.1 lbs./in.
Temperature resistance ⁽¹⁾	min.	-20 °C
	max.	100 °C

⁽¹⁾ Use of the belt with limit values may reduce its life.

 Minimum radius / diameter ⁽²⁾

■ Knife edge minimum radius	no	
■ Bending roller min. diameter	8 mm	0.31 in.
■ Counter-bending roller min. diameter	16 mm	0.63 in.

⁽²⁾ The above mentioned values depend on the type of CHIORINO joint recommended.

Coefficient of friction on driving surface

■ Raw steel sheet	0.20 [-]
■ Laminated plastic/wood	0.25 [-]
■ Steel roller	0.20 [-]
■ Rubberized roller	0.30 [-]

Max. production width 3600 mm 142 in.

SUITABLE FOR

Textile: nonwoven
 Textile: cross-lappers
 Paper industry: tissue
 Tanning industry
 Electronic industry: components conveying


FEATURES

Humidity influence	no
Suitable to metal detector	no
Permanent antistatic dynamically (UNI EN ISO 21179)	yes
Static conductivity (UNI EN ISO 284)	yes
Conveying on skid bed	yes
Conveying on rollers	yes
Conveying on skid bed on top and return	no
Troughed conveying	no
Swan neck conveying	no
Inclined conveying	no
Accumulators belts	yes
Curved conveyor	no
Chemical resistances link	5

COMPLIANCES

REACH EC 1907/2006 Regulation and Amendments

NOTES

Static conductivity (UNI EN ISO 284)
 - Conveying surface 10³ to 10⁵ Ohm per Sqm
 K1% rel. 5 N/mm

Issue: 10-11-2014

Last Update: 08-07-2021

DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.

CODE **NA1255** TYPE **2M10 U0-U2 N HC SP**

Recommended joining procedure **SINGLE Z - 80 x 10 mm**



Other joining methods can be used:

Check our general catalogue to get further info on CHIORINO joining methods.

• Pressing

Heating press **P \ PL \ PLS**

Press settings	
Upper platen temperature	160 °C
Lower platen temperature	160 °C
Temperature gauge setting	160 °C
Curing time in press	0 min.
Pressure	2 bar
Film	TC614 - Film PU black H
Cement	---


1. Use the KM330 thermometer to check the effective temperature inside the belt. Place the thermometer gauge as shown by the drawing at side.



2. Allow the cooling cycle to be completed before removing the belt from the press.

3. A reliable strength of the joint is ensured, providing that temperatures reached by the press are those indicated in the table at side. A periodical inspection of the thermostats is recommended, to make sure they function correctly.

• Layout of components



• Notes

Issued: 10-11-2014

Last Update: 15-11-2018

DISCLAIMER

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.